

ABSTRACT

The present invention provides an adhesive composition which does not contain an organic solvent for use in a dry laminate process for manufacturing artificial leather.

The dry laminate adhesive composition comprises (A) a water-borne polyurethane resin,

5 (B) a cross linking agent, and (C) a thickener, wherein the water-borne polyurethane resin (A) has a softening temperature of less than 80°C and a viscosity of the melt at

80°C of less than 10^5 Pa · s, and wherein a softening temperature of a cured product

obtained after curing a reaction product between the water-borne polyurethane resin (A)

and the crosslinking agent (B) is higher than 120°C.